

PRODUCT DATA SHEET

PRODUCT: Frosted Linen V.B. Latex FORMULA NUMBER: 18Z-581
 CUSTOMER:
 ADDRESS:

OBJECT FINISHED: Sheetrock and wall board

WEIGHT/GALLON:	11.04 lbs.	RECOMMENDED REDUCTION:	None
VISCOSITY:	104-108 KU's	REDUCER:	Water
GRIND:	4 Hegman	REDUCED VISCOSITY:	Use as supplied.
WEIGHT SOLIDS:	47±2%	RECOMMENDED FILM THICKNESS:	
V.O.C.:	1.14 lb./gal.	WET:	6.0-8.0-mils
VOLUME SOLIDS:	30±1%	DRY:	1.7-2.4 mils
COVERAGE:	480 sq.ft.@ 1.0 mil	FLASH TIME:	20 minutes
SUBSTRATE PREP.:	Surface to be painted should be sanded smooth if needed and blown clean of dust and dirt	BAKE TIME:	N/A
APPLICATION METHOD:	Spray, Brush, or Roll	BAKE TEMPERATURE	Air Dry
EQUIPMENT SETTINGS:	For airless spray use 0.021" nozzle and enough air pressure of proper atomization. Roll with ½" nap roller. Do not over roll or spread too thin	OVEN TYPE:	N/A
APPLIED OVER:	Clean sheetrock	GLOSS:	Flat
USED UNDER:	Latex wall paint	HARDNESS:	N/A
		IMPACT RESISTANCE:	N/A

REMARKS: This product was designed for one coat hide with excellent scrub resistance and touch-up qualities. Tested in free films, as per ASTM D-1653, Method A, Condition B, Water Vapor Transmission, this material averages below 0.1 perms.
 Do not use this product if air, paint, or surface temperatures are below 50°F.

DATE ISSUED: 4-29-98

COMPLETED BY:

ARMORCHEM *LLC*
COMBINING TECHNOLOGY FOR THE FUTURE

PRODUCT DATA SHEET